



Production of Aluminium, Bronze and Copper  
in Powder, Paste and Granules

## TECHNICAL DATA SHEET

**revision n°:** 01 (date 4-6-2012), supersedes n°00 (date 10-1-2008)

**Ident. N°:**

**TDS\_S\_EN\_APO\_030\_v01**

**PRODUCT TYPE:** ALUMINIUM POWDER

**PRODUCT NAME:** 030

**PRODUCT DESCRIPTION:** Flake Metal Aluminium Powder

Inspection Criteria	Unit	Lower lim. Value	Upper lim. Value	Test method
<b>Purity of metal</b>	%	99,7	-	
<b>Particle Size Distribution</b>				
<b>D10</b>	µm	1,5	3	laser diffraction by Sympatec HELOS (dry)
<b>D50</b>	µm	6,5	9,5	laser diffraction by Sympatec HELOS (dry)
<b>D90</b>	µm	18	28	laser diffraction by Sympatec HELOS (dry)
<b>Apparent density</b>	g/cm <sup>3</sup>	0,19	0,25	ASTM B212-99
<b>Covering Capacity</b>	cm <sup>2</sup> /g	22000	32000	LCI.002.0

For more information and samples, please contact:

AVL METAL POWDERS nv, Elleboogstraat 7, B-8500 Kortrijk, Belgium, Europe

T +32 (0) 56 22 00 21 - F +32 (0) 56 22 64 14

e-mail: [sales@avlmetalpowders.com](mailto:sales@avlmetalpowders.com)

website: <http://www.avlmetalpowders.com>

VAT BE 0405.375.371 - HR 7 Kortrijk



Please consult AVL website /GENERAL INFO at [www.avlmetalpowders.com](http://www.avlmetalpowders.com) for additional information on our products related to shelf life and storage recommendations .

All data on this technical data sheet are based upon tests and knowledge which our company believes to be currently reliable. Foregoing data is no legal guarantee for specific properties of the product, nor for their suitability for a particular application or process, the liability lies with the buyer. AVL Metal Powders has the right at any time to alter any product data as a result of technical improvements or changes in the manufacturing process.

depart. Name: QC, Stefaan De Forche